

LOCTITE LF 318D

May 2016

PRODUCT DESCRIPTION

LOCTITE LF 318D provides the following product characteristics:

Technology	Solder paste
Application	Pb-free soldering

LOCTITE LF 318D is a halide-free, no clean, low voiding Pb-free solder paste, which has excellent humidity resistance and a broad process window both for printing and reflow. This product has a high tack force to resist component movement during high speed placement and long printer abandon times. LOCTITE LF 318D shows excellent solderability over a wide range of reflow profiles in both air and nitrogen across a wide range of surface finishes including Ni/Au, Immersion Sn, Immersion Ag and OSP copper.

FEATURES AND BENEFITS

- Long print abandon time even on small CSP apertures
- Colorless residues for easy post-reflow inspection
- Suitable for fine pitch, high speed printing up to 150mm/s (6"/s)
- Suitable for enclosed head printing
- Halide-free flux classification: ROL0 to ANSI/J-STD-004

TYPICAL PROPERTIES

Based on Type 3 powder

Solder Paste Typical Properties

Alloys	97SC
Powder Particle Size, μm	20 to 45
Powder Size Coding	AGS
IPC Equivalent	Type 3
Metal Loading (Weight %)	89.0
Slump, J-STD-005, mm	
<i>RT, 15 minutes</i>	
0.33 x 2.03 mm pads	0.06
0.63 x 2.03 mm pads	0.33
<i>150°C, 15 minutes</i>	
0.33 x 2.03 mm pads	0.2
0.63 x 2.03 mm pads	0.33
Brookfield Viscosity TF spindle, 25°C, 5rpm after 2 minutes, mPa·s	855,000
Thixotropic Index (Ti), 25°C ($T_i = \log(\text{viscosity @ } 1.8\text{s}^{-1} / \text{viscosity @ } 18\text{s}^{-1})$)	0.54
Malcom Rheology, 10rpm, 25°C, Rate 6s^{-1}	2,020
Initial tack force, g mm^{-2}	1.5
Useful open time, hours	>24

Solder Powder:

Careful control of the atomisation process for production of solder powders for LOCTITE LF 318D solder pastes ensures that the solder powder is produced to a quality level that exceeds J-STD-006 and EN 29453 requirements for sphericity, size distribution, impurities and oxide levels.

DIRECTIONS FOR USE


Printing:

1. LOCTITE LF 318D is available for stencil printing down to 0.4mm (0.016") pitch QFP devices, with type 3 (AGS) powder.
2. Printing at speeds between 25mm/s (1.0"/s) and 150mm/s (6"/s) can be achieved by using laser cut and electro-polished, electro-formed stencils, metal squeegees (preferably 60°).
3. LOCTITE LF 318D is suitable for use in enclosed head printing systems.


Reflow:

1. Any of the available methods of heating to cause reflow may be used including IR, convection, hot belt, vapor phase and laser soldering.
2. LOCTITE LF 318D is not sensitive to reflow profile type.
3. No single reflow profile is deemed suitable for all processes and applications, but the following example profiles have given good results in practice.

Profile 1:



Profile 2:



Cleaning:

1. LOCTITE LF 318D solder pastes are no-clean and are designed to be left on the PCB in many applications post-assembly since they do not pose a hazard to long-term reliability.
2. Residue removal can be achieved using conventional cleaning processes based on solvents such as MCF800 or suitable saponifying agents.
3. For stencil cleaning and cleaning board misprints, LOCTITE MSC 01 solvent cleaner is recommended.

RELIABILITY PROPERTIES**Solder Paste Medium:**

LOCTITE LF 318D medium includes a stable resin system with slow evaporating solvents and minimal odor. The formulation has been tested to the requirements of the Telcordia (formerly known as Bellcore) GR-78-CORE and ANSI/J-STD-004 for a type ROL0 classification specification.

Test	Specification	Results
Copper Plate Corrosion	ANSI/J-STD-004	Pass
Copper Mirror Corrosion	ANSI/J-STD-004	Pass
Chlorides & Bromides	ANSI/J-STD-004	Pass
Surface Insulation Resistance (without cleaning)	ANSI/J-STD-004 Telcordia GR-78-Core JIS-Z-3248	Pass Pass
Flux Activity Classification (without cleaning)	ANSI/J-STD-004	ROL0

STORAGE AND SHELF LIFE**Storage:**

It is recommended to store LOCTITE LF 318D at 0 to 10°C. (NB cartridges should be stored tip down to prevent the formation of air pockets). The paste should be removed from cold storage a minimum of 4 hours before use. Do not use forced heating methods to bring solder paste up to temperature. LOCTITE LF 318D has been formulated to minimize flux separation on storage but should this occur, gentle stirring for 15 seconds will return the product to its correct rheological performance. To prevent contamination of unused product, do not return any material to its original container.

Shelf Life:

Provided LOCTITE LF 318D is stored tightly sealed in its original container at 0 to 10°C, a minimum shelf life of 183 days can be expected. Air shipment is recommended to minimize the time the containers are exposed to higher temperatures.

DATA RANGES

The data contained herein may be reported as a typical value and/or a range. Values are based on actual test data and are verified on a periodic basis.

GENERAL INFORMATION

For safe handling information on this product, consult the Material Safety Data Sheet (MSDS).

Not for Product Specifications

The technical information contained herein is intended for reference only. Please contact Henkel Technologies Technical Service for assistance and recommendations on specifications for this product.

Conversions

(°C x 1.8) + 32 = °F
 kV/mm x 25.4 = V/mil
 mm / 25.4 = inches
 µm / 25.4 = mil
 N x 0.225 = lb
 N/mm x 5.71 = lb/in
 N/mm² x 145 = psi
 MPa x 145 = psi
 N·m x 8.851 = lb·in
 N·m x 0.738 = lb·ft
 N·mm x 0.142 = oz·in
 mPa·s = cP

Disclaimer**Note:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 0.1

Americas
+1.888.943.6535

Europe
+32.1457.5611

Asia
+86.21.3898.4800

For the most direct access to local sales and technical support visit: www.henkel.com/electronics